


Technical Data Sheet Coating-Yellow 74 (JA)

Product Description			
Reference	J-JHY 7400L		
Color Index	Pigment Yellow 74	CAS No.	6358-31-2
CI No.	22829	Chemical Class	BIS azo
EINECS No.	228-768-4	REACH-No.	01-2119456819-22-XXXX

Physical Properties	
Specific Surface (m ² /g)	55
Density (g/cm ³)	1.5
Oil Absorption (ml/100g)	45

Chemical Resistance (1-5)	
Acid Resistance	5
Alkali Resistance	5

Applications		
Automotive Paints	OEM	•
	Refinish	•
	Water-based	•
Industrial paints	Solvent-based	-
	Water-based	-
	Amine-curing epoxy	-
	Coil coatings	o
	Powder coatings	-
Decorative paints	Solvent-based	o
	Water-based	o



• Recommended o Limited suitability - Not recommended

Fastness Properties		°C	1-8	1-5	1-5
		Heat resistance	Lightfastness	Weathering	Fastness to overpainting
Alkyd/melamine	Full Shade	160	7	4	4
	1:10 TiO ₂	160	6	3	3

Fastness to Solvents (1-5)							
Water	Butanol	Xylene	Butyl glycol	White spirit	Butyl acetate	Methylethyl ketone	Dibutylphthalate
-	3	4	-	4	2-3	4	-



FALCONE
SPECIALITIES

Note

The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colorant shade.

Contact

Falcone Specialities Ltd.
Riedthofstrasse 212 – 8105 Regensdorf – Switzerland
welcome@falcone.ch – www.falcone-specialities.com
Hotline: +41 44 525 01 80



Last Update

24.01.2020

